

Hemicellulose Content Assay Kit

Note: Take two or three different samples for prediction before test.

Operation Equipment: Spectrophotometer/ Microplate reader

Cat No: AK0060

Size: 100T/96S

Components:

Extract solution 1: 60 mL × 1, stored at room temperature;

Extract solution 2: 60 mL × 1 bottle, stored at room temperature;

Reagent 1: 100 mL of 80% ethanol x 1, prepared by yourself;

Reagent 2: 10 mL × 1, stored at 4 ° C;

Standard: powder × 1, 10 mg of D-xylose, stored at 4C. Just before use, add 1 mL of distilled water to dissolve to prepare a standard solution of 10 mg/mL.

Product Description:

Hemicellulose refers to the part of plant polysaccharide that is symbiotic with cellulose in the cell wall of plants and soluble in alkaline solutions. It is much easier to hydrolyze than cellulose after encountering acid. It is widely present in plants. Its distribution varies greatly depending on plant species, maturity, morning and evening wood, cell types and their morphological parts. A plant often contains several hemicellulose composed of two or three sugar groups. Hemicellulose has different chemical structure. Hemicellulose is a new type of available energy source.

Required material

Desk centrifuge, scales, spectrophotometer/microplate reader, constant temperature water bath, mortar/homogenizer, micro glass cuvette/96 well plate, transferpeltor, sieve, EP tube and distilled water.

Procedure:

I. Sample processing:

Samples are air-dried or oven-dried to constant weight. After the mortar is fully ground, pass through a 30-50 mesh sieve.

II. Determination procedure:

- 1 Preheat the spectrophotometer/microplate reader 30min, adjust wavelength to 540nm, set zero with distilled water.
- 2 Dilute the standard with distilled water to 1 、 0.9 、 0.8 、 0.6 、 0.4 、 0.2 mg/mL standard solution.
- 3 Add reagents with the following list:

Reagent name	Blank tube (B)	Test tube(T)	Standard tube(S)
Sample (g)		0.05	
Reagent 1 (μL)		1000	
Vortex to mix, place in a water bath at 90C for 10 min, and centrifuge at 8000 g for 10 min at			

25C. Discard the supernatant and leave the pellet.			
Distilled water (μL)		1000	
Vortex, centrifuge at 8000 g for 10 min at 25C, discard the supernatant, repeat this step three times, take the pellet, and dry to constant weight.			
Extract solution 1 (μL)	500	500	
Place in 90C water bath for 1 h, then naturally cooled to room temperature.			
Extract solution 2 (μL)	500	500	
Vortex, centrifuge at 8000 g for 10 min at 25C, and take the supernatant for measurement.			
Supernatant (μL)	80	80	
Standard solution (μL)			80
Reagent 2 (μL)	80	80	80
Distilled water (μL)	160	160	160
Vortex to mix, place in a water bath at 90C for 5 minutes, and cool to room temperature			
Take 200 μL of the reaction solution in a micro glass cuvette/96-well plate, and measure the absorbance A at 540 nm, and record it as A _S , A _T , and A _B , and calculate $\Delta A_S = A_S - A_B$, $\Delta A_T = A_T - A_B$.			

Note:

- 1. The blank tube only needs to be measured 1-2 times;**
- 2. It is recommended to dilute the supernatant after adding the extract solution 2 and centrifugation for 10-20 times to test. In the formula, pay attention to multiply by the dilution factor.**

III. Calculation:

- 1 Standard curve drawing:

Taking the concentration of each standard solution as the x-axis and its corresponding ΔA_S as the y- axis, draw a standard curve to get the standard equation $y = kx + b$, and bring ΔA into the equation to get x (mg/mL). Calculated by micro quartz cuvette

- 2 Calculation of hemicellulose content

$$\text{Hemicellulose content (mg / g dry weight)} = x \times V_{TS} \div W \times F = x \div W \times F$$

V_{TS} : volume of extraction solution added, 1 mL;

W: sample weight, g;

F: dilution factor.

Note

1. If the measured absorbance value exceeds the absorbance value in the linear range, you can increase the sample volume or dilute the sample before performing the measurement.
2. It is recommended to dilute the supernatant (adding extract 2 and centrifuge) by 10-20 times before testing. Pay attention to multiply by the dilution factor in the calculation formula.



Related Products:

AK0139/AK0138 Glycogen synthase(GCS) Activity Assay Kit

AK0137/AK0136 UDP-glucose pyrophosphosphprylase(UGP) Activity Assay Kit

AK0088/AK0087 N-Acetyl- β -D-Glucosidase(NAG) Activity Assay Kit

Technical Specifications:

Minimum Detection Limit: 0.1516mg/mL

Linear Range: 0.2-1 mg/mL